SHINITE® PBT

ENGINEERING PLASTIC DIVISION

SHINKONG INDUSTRY (HANGZHOU) CO., LTD.

新光工业(杭州)有限公司

No.1-2, Auenue 6, Economy & Technology Development Zone, Hangzhou City, Zhejiang, P.R. China TEL:0571-56755777 Fax: 0571-86912438

Technical Data

SHINITE[®] D201G20NA

GF Grade / 玻纤强化级: DH8020

		Unit	Test Method	Values
Mechanical properties	机械性质			
Izod Impact(Notched)	冲击强度	Kg-cm/cm	ASTM D256	7.2
Tensile Strength	拉伸强度	Kg/cm ²	ASTM D638	1169
Elongation	拉伸率	%	ASTM D638	3.9
Flexural Strength	弯曲强度	Kg/cm ²	ASTM D790	1880
Flexural Modulus	弯曲模数	Kg/cm ²	ASTM D790	67400
Thermal properties	热性质			
Heat Deflection Temperature	热变形温度		ASTM D648	
66psi		$^{\circ}\mathrm{C}$		-
264psi		$^{\circ}\mathrm{C}$		207
Flammability	防火性	-	UL94	НВ
Melting Point	熔点	$^{\circ}\mathrm{C}$	DSC	223
Electrical properties	电气性质			
Dielectric Strength	介电强度	KV/MM	ASTM D149	15
Dielectric Constant	介电常数		ASTM D150	3
Volume Resistivity	体积电阻	Ω -CM	ASTM D257	1.00E+16
Other properties	其它性质			
Specific Gravity	比重	-	ASTM D792	1.449
Water Absorption	吸水率	%	ASTM D570	0.07
Mold Shrinkage	成形收缩率		ASTM D955	
Flow	流动方向	%		0.3~0.5
Cross Flow	垂直方向	%		0.5~0.9
Volume Resistivity Other properties Specific Gravity Water Absorption Mold Shrinkage Flow	体积电阻 其它性质 比重 吸水率 成形收缩率 流动方向	Ω -CM - %	ASTM D257 ASTM D792 ASTM D570	1.00E+16 1.449 0.07 0.3~0.5

"Nothing in this information shall be construed as a recommendation for any use that may infringe on any patent right or as an endorsement of any material supplied by Shinkong Synthetic Fibers Corporation. We do not gurantee the applicability or the accuracy of this information or the performance of our products in any specific situation. We recommend each user of our products make its own tests to determine if the material is suitable for a particular use. The data show here are within the normal range of product properties, but they are NOT SECIFICATION LIMITS. Additives of any kind alter some or all of the properties."